

Contract No. W-7405-eng-26

METALS AND CERAMICS DIVISION

CATASTROPHIC CORROSION OF TYPE 304 STAINLESS STEEL IN A
SYSTEM CIRCULATING FUSED SODIUM FLUOROBORATE

J. W. Koger and A. P. Litman

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.


As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

JANUARY 1970

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee
operated by
UNION CARBIDE CORPORATION
for the
U.S. ATOMIC ENERGY COMMISSION


DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

fy



CONTENTS

	Page
Abstract	1
Introduction	1
Results	3
Visual and Metallographic	3
Chemical	6
Physical Property Changes	10
Discussion	11
Impurity Effects	12
Effect of Imposed Electromotive Force	12
Stainless Steel Corrosion	12
Dissimilar-Metal Corrosion	14
Corrosion Mechanism and Mode	14
Summary	16
Conclusions	16
Recommendations	16



CATASTROPHIC CORROSION OF TYPE 304 STAINLESS STEEL IN A
SYSTEM CIRCULATING FUSED SODIUM FLUOROBORATE

J. W. Koger and A. P. Litman

ABSTRACT

A type 304 stainless steel liquid level probe contacted fluoroborate salt (NaBF_4 -8 mole % NaF) in an Inconel 600 pump loop at constant temperatures in the range 540 to 690°C for 192 hr. The probe exhibited heavy attack, evidenced by severe leaching of Cr, Fe, Mn, and Si from the alloy. Equivalent uniform attack was about 4 mils/day. Corrosion of the stainless steel, which is inferior to nickel-base alloys in fused fluorides, became catastrophic in this system due to dissimilar-metal effects.

INTRODUCTION

The PKP-1 loop, constructed of Inconel 600, is a forced-circulation loop and part of the Fuel Pump High Temperature Endurance Test Facility. The loop is used for performance testing centrifugal pumps of the type developed for the Molten-Salt Reactor Experiment (MSRE). The loop was altered to accept NaBF_4 -8 mole % NaF as the circulating medium as part of the program to qualify the salt for use as a coolant in molten-salt reactors. The experimental program currently involves the measurement of the cavitation pressure of the pump as a function of temperature of the molten salt. For these experiments the loop is operated under nearly isothermal conditions in the range 540 to 690°C.

A liquid-level probe (Fig. 1) was installed in the pump bowl of PKP-1 on June 20, 1968, to indicate changes in the liquid level that occurred independently of changes in salt density. The probe was initially thought to be constructed with an Inconel 600 outer sheath, but later examination showed it was type 304 stainless steel. The instrument used a 1000-Hz electrical signal across a conductance probe immersed in the salt and had an output signal that was a linear function

Photo 75764




Fig. 1. Liquid-Level Probe
Exposed to NaBF_4 -8 mole % NaF in
PKP-1 Loop for 192 hr at 540 to
690°C.

of immersion depth.¹ The salt temperatures seen by the probe are given in Table 1. Signals from the probe stopped shortly after installation. The probe was removed on June 28, 1968, after 192 hr in the salt, and extensive corrosion had obviously occurred. This paper describes our metallurgical analysis of the probe, discusses the corrosion phenomena that occurred, and details the significance of the incident for the Molten-Salt Reactor Program.

Table 1. Salt Temperatures in
MSRP-PKP-1 Pump Loop

Duration (hr)	Temperature (°C)
21	540
92	552
26	649
53	690

RESULTS

Visual and Metallographic

The portion of the probe that was immersed in salt was 0.25 in. in diameter \times 0.030 in. wall thickness. As shown in Fig. 2, heavy attack occurred over the lower 2 in. of this section. The level of the salt on the probe during operation is not known and appears to have varied. For analysis, the tubing was cut into eight 3/4-in.-long samples, numbered such that sample 1 was furthest from the exposed end.

Figure 3 shows two magnified views of the end of the probe (sample 8). Severe distortion and very large pits are seen. In some places the wall was completely penetrated. We calculated that the corrosion in this region was equivalent to a uniform attack of 3.75 mils/day (1.4 in./year). Damage decreased with increasing distance from the probe

¹Private communication, A. N. Smith, ORNL, to J. W. Koger, 1968.




Fig. 2. Lower End of Liquid-Level Probe that Contacted NaBF_4 -8 mole % NaF in PKP-1 Loop for 192 hr at 540 to 690°C. (a) Entire active length. (b) Bottom 2 in.




Fig. 3. Tip of the Liquid-Level Probe.

tip. Pitting was less severe on sample 7 (about 1 in. from the tip), but the photomicrographs (Fig. 4) show that this area was also heavily attacked. The attack in this region extended for about 20 mils through the tubing (about 3 mils/day). Figure 5, a photomicrograph of the upper end of sample 7, shows a preferential attack in the grain boundaries, with the voids linking to form holes. Here the attack only extends for about 10 mils through the tubing, thus, demonstrating the varying level of the salt, as indicated by corrosion, on the probe.

Chemical

The salt was chemically analyzed just before the probe was placed in the system and just after it was removed. The results are given in Table 2. The Li, Be, U, and Th are from an earlier fuel salt used in this loop. As expected, no significant changes in the amounts of the corrosion products in the salt resulted from corrosion of the probe because (1) the surface area of the probe was small compared to that of the loop, and (2) the volume of salt was large compared to the quantity of corrosion products removed. The reported changes in the iron and oxygen concentrations are attributed to sampling and analytical procedures.

Each probe sample was analyzed, and the results are given in Table 3. We removed the attacked area from the base metal on sample 8 and determined the composition of each region. We found that the base material of the probe was type 304 stainless steel and not Inconel 600 as originally thought by project personnel. The analysis of the attacked area disclosed that mainly Cr, Fe, Mn, and Si had been leached from the base metal by the salt. This removal resulted in an apparent enrichment in Ni, Mo, and Cu, although in the areas of complete dissolution, of course, all the alloying elements were removed. Also, about 20% unidentified material was associated with the attacked area.





Fig. 4. Microstructure of Lower End of Sample 7. (a) 100x.
(b) 500x.





Fig. 5. Microstructure of Upper End of Sample 7. (a) 100X.
(b) 500X.

Table 2. Analysis of Fluoroborate Salt in PKP-1^a

Element	Content, ppm		Element	Content, wt %	
	Before Insertion	After Removal		Before Insertion	After Removal
Cr	97	93	Na	21.0	21.5
Fe	272	229	B	9.18	9.31
Ni	27	25	F	66.7	65.9
O	1149	380	Li	0.182	0.193
			Be	0.18	0.19
			U	0.229	0.241
			Th	0.170	0.172

^aWater content not analyzed.

Table 3. Chemical Composition of Sections of Type 304 Stainless Steel Liquid-Level Probe in PKP-1 Loop

Sample	Portion Analyzed	Content, %						
		Cr	Fe	Ni	Mn	Mo	Si	Cu
		<u>Before Test</u>						
Nominal composition type 304 stainless steel		18-20	Major	8-10	1.5		0.6	
		<u>After Test</u>						
1	Base metal	18	69	9.4	1.4	0.14	0.52	0.12
2	and layer,	17	68	8.1	1.3	0.14	0.44	0.10
3	if any	17	68	11.0	1.4	0.14	0.58	0.12
4		17	68	11.7	1.4	0.13	0.64	0.12
5		16	67	11.2	1.3	0.11	0.70	0.10
6		16	67	9.0	1.2	0.12	0.46	0.10
7		16	67	10.2	1.3	0.12	0.52	0.11
8	Base metal	18	69	10.0	1.7	0.15	0.60	0.10
8	Attacked layer	1	15	60.0	0.1	1.00	0.27	0.50

Physical Property Changes

Initial examination disclosed that some parts of the probe were highly ferromagnetic. Each of the eight samples was tested with a Radio Frequency Laboratory gaussmeter No. 1890 to determine its magnetic field strength (Table 4). This is a rapid nondestructive test suitable for many engineering systems. This device is quite useful on iron- or nickel-base alloys that are selectively attacked enough to change their magnetic properties. The magnetic field strength of the samples increased as the end of the probe was approached.

Table 4. Magnetic Field Strength and Seebeck Effect

Sample	B (gauss)	Seebeck Effect (instrument units)
1	0.20	5.0
2	0.20	7.5
3	0.20	10.0
4	0.30	9.5
5	0.50	11.5
6	0.75	13.5
7	2.00	14.0
8	Too fragile to be measured but highly ferromagnetic	Too fragile
<u>Standards</u>		
Monel	0.20	>30
Nickel	0.50	27
Type 304 stain- less steel	0.06	8.5
Inconel	0.04	-13.0
Hastelloy N	0.06	-11.5

Another testing device utilized in this study was a metal comparison meter.² This instrument nondestructively identifies metals by measuring the Seebeck effect³ of the unknown metal and comparing the value to that obtained from a piece of known metal. The standards built into the device are nickel, type 304 stainless steel, Monel, Inconel 600, and Hastelloy N. Table 4 gives the relative Seebeck effect readings for the various samples and the standards. No attempt was made to determine absolute values. The examination results were that the Seebeck effect increased as the end of the probe was approached, in agreement with the gaussmeter tests.

The metallurgical evaluation showed that the attack by the fluoroborate salt drastically changed the composition and properties of the type 304 stainless steel probe during service. The highly attacked region had a final composition near that of 78 Permalloy (Ni-22% Fe), a highly ferromagnetic material. The changes of the magnetic field strength and the Seebeck effect as a function of attack were also indicative of composition changes and are often more sensitive to small composition changes than chemical analysis. The gradation in these properties along the probe, as opposed to an abrupt change, indicates that the salt level varied during exposure.

DISCUSSION

To account for the heavy attack observed, we considered several potential corrosion mechanisms.

²Private communication, J. Summers, Y-12, to J. W. Koger, 1968.

³The Seebeck effect is the phenomenon of a current passing between two metal junctions held at different temperatures, when no other source of emf is present. The actual measuring unit consists of two copper probes, one of which is heated, and a millivoltmeter. The probes are placed on the metal to be tested, and the induced emf is read.

Impurity Effects

Salt analyses were obtained to decide if the salt itself was excessively corrosive. Past work⁴ has shown that fluoroborates that contain at least 2000 ppm water and oxygen are highly corrosive to iron- and nickel-base alloys. These impurities react with the salt to form HF, which attacks almost all the constituents of the container materials. The most common evidence of this is detection of an increase in the concentration of the more noble elements, such as nickel, in the salt. This was not found for the system here, so we conclude, even considering the surface area and volume mismatch of probe to salt and container system, that the impurity effects on the probe corrosion were small.

Effect of Imposed Electromotive Force

We also believe that the passage of current through the probe and the associated emf had no effect on the corrosion rate, since other probes containing essentially the same elements in different combinations have shown no deleterious effects under an imposed emf in prior exposures to fused fluorides.⁵

Stainless Steel Corrosion

In the last two decades a continuing corrosion program at ORNL has been seeking to determine the compatibility of various fused fluoride mixtures with nickel- and iron-base alloys.⁴⁻¹⁰ Most of these tests

⁴J. W. Koger and A. P. Litman, Compatibility of Hastelloy N and Croloy 9M with NaBF₄-NaF-KBF₄ (90-4-6 mole %) Fluoroborate Salt, ORNL-TM-2490 (April 1968).

⁵J. W. Koger, unpublished data from MSRP Natural Circulation Loop Corrosion Program, 1967 through 1969.

⁶G. M. Adamson, R. S. Crouse, and W. D. Manly, Interim Report on Corrosion by Alkali-Metal Fluorides: Work to May 1, 1953, ORNL-2337 (March 20, 1959). Declassified May 9, 1959.

⁷G. M. Adamson, R. S. Crouse, and W. D. Manly, Interim Report on Corrosion by Zirconium-Base Fluorides, ORNL-2338 (Jan. 3, 1961).

have used natural-circulation loops as the testing device. No tests have been conducted to determine the compatibility of stainless steel with fluoroborate salts, although both stainless steels and fluoroborate salt have been separately tested with other materials.

Table 5 summarizes recent data^{9,10} obtained from natural-circulation loop tests and compares the compatibilities of some fluoride salts with type 304 stainless steel and with Hastelloy N. In 5000-hr tests Hastelloy N loses about seven times as much weight in NaBF₄-8 mole % NaF, 4 mg/cm², as it does in lithium-beryllium type fuel salt, 0.6 mg/cm². By analogy and with knowledge of the modes and mechanisms of fluoroborate salt corrosion, we assume that type 304 stainless steel exposed to the same fluoroborate salt for 5000 hr at 605°C in an all-stainless-steel system would lose about seven times as much weight as in a

⁸J. H. DeVan and R. B. Evans III, Corrosion Behavior of Reactor Materials in Fluoride Salt Mixtures, ORNL-TM-328 (September 19, 1962).

⁹J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Feb. 29, 1968, ORNL-4254, pp. 218-225.

¹⁰J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Aug. 31, 1968, ORNL-4344, pp. 257-266.

Table 5. Weight Loss of Alloys Exposed to Various Salts at Different Temperatures for 5000 hr

Metal	Salt	Maximum Temperature (°C)	ΔT (°C)	Weight Loss (mg/cm ²)	Uniform Loss (mils/year)
Hastelloy N	LiF-BeF ₂ -ThF ₄ (73-2-25 mole %)	675	55	0.4	0.03
Hastelloy N	LiF-BeF ₂ -UF ₄ (65.5-34.0-0.5 mole %)	705	170	0.6	0.05
Hastelloy N	NaBF ₄ -NaF (92-8 mole %)	605	145	4.0	0.3
Type 304 stainless steel	LiF-BeF ₂ -ZrF ₄ -UF ₄ -ThF ₄ (70-23-5-1-1 mole %)	675	100	25.0	1.8
Type 304 stainless steel	NaBF ₄ -NaF (92-8 mole %)	538-690		175.0	12.6

^aEstimated from comparison with the behavior of Hastelloy N in NaBF₄-8 mole % NaF of the same impurity level and assuming an all-stainless-steel system.

lithium-beryllium type fuel salt; that is, 175 vs 25 mg/cm². Corrosion of this magnitude would be severe, equivalent to about 13 mils/year (0.035 mil/day) attack, more than can be tolerated in a molten-salt reactor. However, this rate is only 1% of the maximum corrosion rate, 1.4 in./year (1370 mils/year) experienced by the probe.

Dissimilar-Metal Corrosion

It should be noted that the above comparison of corrosion rates of stainless steel and Hastelloy N is really valid only in systems where all the container material exposed to the salt is of the same composition. In the PKP-1 system described in this work, the iron-base type 304 stainless steel was surrounded by the more noble and more corrosion resistant nickel-base Inconel 600, which can be assumed to set the oxidizing potential of the system. Thus, it is not surprising that the less noble and more active stainless steel underwent much more corrosion (1370 vs 13 mils/year) than it would had the entire system been stainless steel. This well-known effect is termed dissimilar-metal corrosion and has been noted in both salt and liquid metal systems.^{10,11}

Corrosion Mechanism and Mode

Our interpretation of the catastrophic corrosion that occurred selectively on austenitic stainless steel in this dissimilar-metal test system is consistent with related thermodynamic and electrochemical phenomena. Examination of Table 6 shows that the elements removed from the stainless steel are those whose fluorides are more stable than NiF₂. This is in agreement with Bakish and Kern¹² who found almost all the chromium and most of the iron removed from Inconel 600 exposed to 20% K₂TaF₇ in equimolar KCl-NaCl at 800°C. Measuring galvanic cells with a molten KCl-NaCl-KF electrolyte, they found the nickel electrode

¹¹J. H. DeVan, A. P. Litman, J. R. DiStefano, and C. E. Sessions, Lithium and Potassium Corrosion Studies with Refractory Metals, ORNL-TM-1673 (December 1966).

¹²R. Bakish and F. Kern, "Selective Corrosion of Inconel," Corrosion **16**, 553t (1960).

Table 6. Relative Stability of Fluorides^a

Compound	Free Energy of Formation at 1000°K (kcal/gram-atom F)
SiF ₄ ^b	-84
MnF ₂ ^b	-79
CrF ₂ ^b	-75
FeF ₂ ^b	-68
NiF ₂	-61
MoF ₆	-58
CuF ₂	-49

^aBased on A. Glassner, The Thermochemical Properties of the Oxides, Fluorides and Chlorides to 2500°K, ANL-5750 (1957).

^bCompounds of the metals known to be removed from the stainless steel (Table 3).

more noble than iron by 0.3 v and chromium by 0.7 v. Recent ORNL measurements¹³ of electrode potentials in molten fluorides agree qualitatively with Bakish and Kern's data and our corrosion results.

Thus, it is clear that the corrosive action of a fluoride salt on an alloy with or without dissimilar-metal mass transfer is fundamentally an electrochemical process wherein some or all of the alloy constituents are oxidized to their ionic state with the formation of fluoride compounds. The rate may be controlled by either solid-state diffusion or boundary-layer diffusion, with the attack concentrated at regions of highest energy, such as grain boundaries, subgrain boundaries, certain crystallographic planes, and dislocations.

¹³H. W. Jenkins, G. Mamantov, and D. L. Manning, "Electrode Potentials of Several Redox Couples in Molten Fluorides," Journal of the Electrochemical Society, in press.

Summary

The severe corrosion of type 304 stainless steel exposed to a fluoroborate salt in an Inconel 600 system was interpreted. Drawing analogies from similar systems we conclude that the main cause of the catastrophic corrosion was dissimilar-metal corrosion. The stainless steel was the least noble part of the test system and thus suffered the brunt of the attack. However, we believe that the corrosion of stainless steel in an all-stainless-steel system by fused fluoroborate salt of the impurity level that existed in this case would still be excessive. We showed that from comparison of free energies and electrode potentials one can predict the relative stability of the constituents of an alloy in fused fluorides.


CONCLUSIONS

1. Type 304 stainless steel in an Inconel 600 system in the temperature range 540 to 690°C was severely corroded by NaBF_4 -8 mole % NaF.
2. The fact that the type 304 stainless steel was the least noble part of an Inconel 600 system increased the amount of corrosion.
3. The mode of attack involves leaching large quantities of Cr, Fe, Mg, and Si from the stainless steel, leaving a highly ferromagnetic nickel alloy.
4. The order of element removal in type 304 stainless steel by the fused sodium fluoroborate salt is in agreement with electrode potential measurements and free energy data in other halide salt systems and also is in agreement with other corrosion studies.
5. Type 304 stainless steel in an all-stainless-steel system exposed to fluoroborate salt of the impurity level used in these experiments would corrode too much to be useful in engineering systems.

RECOMMENDATIONS

1. This experience emphasizes the necessity for more careful control over materials being placed in a system containing a relatively uncharacterized fused fluoride salt.

2. In our judgment, low corrosion in nickel- and iron-containing alloys is favored by decreasing chromium and iron concentrations; that is, in order of decreasing corrosion resistance, we find modified Hastelloy N (containing no iron), Hastelloy N, Inconel 600, and stainless steel. While the general use of Hastelloy N alloys in the Inconel PKP-1 loop service is recommended, dissimilar-metal corrosion effects prohibit the use of any alloy less noble than Inconel 600.



INTERNAL DISTRIBUTION

- 1-3. Central Research Library
- 4-5. ORNL Y-12 Technical Library
Document Reference Section
- 6-25. Laboratory Records
26. Laboratory Records, ORNL RC
27. ORNL Patent Office
28. R. K. Adams
29. G. M. Adamson, Jr.
30. R. G. Affel
31. J. L. Anderson
32. R. F. Apple
33. W. E. Atkinson
34. C. F. Baes
35. J. M. Baker
36. S. J. Ball
37. C. E. Bamberger
38. C. J. Barton
39. H. F. Bauman
40. M. S. Bautista
41. S. E. Beall
42. R. L. Beatty
43. M. J. Bell
44. M. Bender
45. C. E. Bettis
46. E. S. Bettis
47. D. S. Billington
48. R. E. Blanco
49. F. F. Blankenship
50. J. O. Blomeke
51. E. E. Bloom
52. R. Blumberg
53. E. G. Bohlmann
54. B. S. Borie
55. C. J. Borkowski
56. H. I. Bowers
57. C. M. Boyd
58. G. E. Boyd
59. J. Braunstein
60. M. A. Bredig
61. R. B. Briggs
62. H. R. Bronstein
63. G. D. Brunton
64. O. W. Burke
65. S. Cantor
66. D. W. Cardwell
67. J. H. Carswell, Jr.
68. W. L. Carter
69. G. I. Cathers
70. J. E. Caton
71. O. B. Cavin
72. J. M. Chandler
73. C. J. Claffey
74. F. H. Clark
75. H. D. Cochran
76. Nancy Cole
77. C. W. Collins
78. E. L. Compere
79. K. V. Cook
80. W. H. Cook
81. J. W. Cooke
82. L. T. Corbin
83. B. Cox
84. J. L. Crowley
85. F. L. Culler
86. D. R. Cuneo
87. J. E. Cunningham
88. J. M. Dale
89. D. G. Davis
90. R. J. DeBakker
91. J. H. DeVan
92. J. R. DiStefano
93. S. J. Ditto
94. F. A. Doss
95. A. S. Dworkin
96. W. P. Eatherly
97. J. R. Engel
98. E. P. Epler
99. J. I. Federer
100. D. E. Ferguson
101. L. M. Ferris
102. A. P. Fraas
103. J. K. Franzreb
104. H. A. Friedman
105. D. N. Fry
106. J. H. Frye, Jr.
107. L. C. Fuller
108. W. K. Furlong
109. C. H. Gabbard
110. R. B. Gallaher
111. R. E. Gehlbach
112. J. H. Gibbons
113. L. O. Gilpatrick

114. G. Goldberg
 115. W. R. Grimes
 116. A. G. Grindell
 117. R. W. Gunkel
 118. R. H. Guymon
 119. J. P. Hammond
 120. R. L. Hammer
 121. T. H. Handley
 122. B. A. Hannaford
 123. P. H. Harley
 124. D. G. Harman
 125. W. O. Harms
 126. C. S. Harrill
 127. P. N. Haubenreich
 128. F. K. Heacker
 129. R. E. Helms
 130. P. G. Herndon
 131. D. N. Hess
 132. J. R. Hightower
 133-135. M. R. Hill
 136. E. C. Hise
 137. B. F. Hitch
 138. H. W. Hoffman
 139. D. K. Holmes
 140. P. P. Holz
 141. R. W. Horton
 142. A. Houtzeel
 143. T. L. Hudson
 144. W. R. Huntley
 145. H. Inouye
 146. W. H. Jordan
 147. P. R. Kasten
 148. R. J. Kedl
 149. C. W. Kee
 150. M. T. Kelley
 151. M. J. Kelly
 152. C. R. Kennedy
 153. T. W. Kerlin
 154. H. T. Kerr
 155. J. J. Keyes
 156. R. T. King
 157. S. S. Kirslis
 158. L. R. Koffman
 159-163. J. W. Koger
 164. H. W. Kohn
 165. R. B. Korsmeyer
 166. A. I. Krakoviak
 167. T. S. Kress
 168. J. W. Krewson
 169. C. E. Lamb
 170. J. A. Lane
 171. M. S. Lin
 172. R. B. Lindauer
 173-177. A. P. Litman
 178. E. L. Long, Jr.
 179. A. L. Lotts
 180. M. I. Lundin
 181. R. N. Lyon
 182. R. L. Macklin
 183. H. G. MacPherson
 184. R. E. MacPherson
 185. J. C. Mailen
 186. D. L. Manning
 187. C. D. Martin
 188. W. R. Martin
 189. R. W. McClung
 190-194. H. E. McCoy
 195. D. L. McElroy
 196. C. K. McGlothlan
 197. C. J. McHargue
 198. H. A. McLain
 199. B. McNabb
 200. L. E. McNeese
 201. J. R. McWherter
 202. H. J. Metz
 203. A. S. Meyer
 204. R. L. Moore
 205. C. A. Mossman
 206. D. M. Moulton
 207. T. R. Mueller
 208. M. L. Myers
 209. H. H. Nichol
 210. J. P. Nichols
 211. E. L. Nicholson
 212. T. S. Noggle
 213. L. C. Oakes
 214. S. M. Ohr
 215. P. Patriarca
 216. A. M. Perry
 217. T. W. Pickel
 218. H. B. Piper
 219. C. B. Pollock
 220. B. E. Prince
 221. G. L. Ragan
 222. J. L. Redford
 223. J. D. Redman
 224. D. M. Richardson
 225. M. Richardson
 226. G. D. Robbins
 227. R. C. Robertson
 228. K. A. Romberger
 229. M. W. Rosenthal

- | | | | |
|------|------------------|------|------------------|
| 230. | R. G. Ross | 257. | W. Terry |
| 231. | J. Roth | 258. | R. E. Thoma |
| 232. | J. P. Sanders | 259. | P. F. Thomason |
| 233. | H. C. Savage | 260. | L. M. Toth |
| 234. | W. F. Schaffer | 261. | A. L. Travaglini |
| 235. | C. E. Schilling | 262. | D. B. Trauger |
| 236. | Dunlap Scott | 263. | Chia-Pao Tung |
| 237. | J. L. Scott | 264. | W. E. Unger |
| 238. | H. E. Seagren | 265. | G. M. Watson |
| 239. | C. E. Sessions | 266. | J. S. Watson |
| 240. | J. H. Shaffer | 267. | H. L. Watts |
| 241. | W. H. Sides | 268. | C. F. Weaver |
| 242. | G. M. Slaughter | 269. | B. H. Webster |
| 243. | A. N. Smith | 270. | A. M. Weinberg |
| 244. | F. J. Smith | 271. | J. R. Weir |
| 245. | G. P. Smith | 272. | K. W. West |
| 246. | O. L. Smith | 273. | H. L. Whaley |
| 247. | P. G. Smith | 274. | M. E. Whatley |
| 248. | I. Spiewak | 275. | J. C. White |
| 249. | R. C. Steffy | 276. | R. P. Wichner |
| 250. | H. H. Stone | 277. | L. V. Wilson |
| 251. | R. A. Strehlow | 278. | Gale Young |
| 252. | R. D. Stulting | 279. | H. C. Young |
| 253. | D. A. Sundberg | 280. | J. P. Young |
| 254. | R. W. Swindeman | 281. | E. L. Youngblood |
| 255. | J. R. Tallackson | 282. | F. C. Zapp |
| 256. | E. H. Taylor | | |

EXTERNAL DISTRIBUTION

- | | |
|----------|--|
| 283. | G. G. Allaria, Atomics International |
| 284. | J. G. Asquith, Atomics International |
| 285. | D. F. Cope, RDT, SSR, AEC, Oak Ridge National Laboratory |
| 286. | C. B. Deering, AEC, OSR, Oak Ridge National Laboratory |
| 287. | A. R. DeGrazia, AEC, Washington |
| 288. | H. M. Dieckamp, Atomics International |
| 289. | David Elias, AEC, Washington |
| 290. | A. Giambusso, AEC, Washington |
| 291. | J. E. Fox, AEC, Washington |
| 292. | F. D. Haines, AEC, Washington |
| 293. | C. E. Johnson, AEC, Washington |
| 294. | W. L. Kitterman, AEC, Washington |
| 295. | W. J. Larkin, AEC, Oak Ridge Operations |
| 296. | Kermit Laughon, AEC, OSR, Oak Ridge National Laboratory |
| 297. | C. L. Matthews, AEC, OSR, Oak Ridge National Laboratory |
| 298-299. | T. W. McIntosh, AEC, Washington |
| 300. | A. B. Martin, Atomics International |
| 301. | D. G. Mason, Atomics International |
| 302. | G. W. Meyers, Atomics International |
| 303. | D. E. Reardon, AEC, Canoga Park Area Office |

- 304. D. R. Riley, AEC, Washington
- 305. H. M. Roth, AEC, Oak Ridge Operations
- 306. M. Shaw, AEC, Washington
- 307. J. M. Simmons, AEC, Washington
- 308. T. G. Schleiter, AEC, Washington
- 309. W. L. Smalley, AEC, Washington
- 310. S. R. Stamp, AEC, Canoga Park Area Office
- 311. E. E. Stansbury, the University of Tennessee
- 312. D. K. Stevens, AEC, Washington
- 313. R. F. Sweek, AEC, Washington
- 314. A. Taboada, AEC, Washington
- 315. M. J. Whitman, AEC, Washington
- 316. R. F. Wilson, Atomics International
- 317. Laboratory and University Division, AEC, Oak Ridge Operations
- 318-332. Division of Technical Information Extension