

Contract No. W-7405-eng-26

METALS AND CERAMICS DIVISION

COMPATIBILITY OF FUSED SODIUM FLUOROBORATES AND  $\text{BF}_3$  GAS  
WITH HASTELLOY N ALLOYS

J. W. Koger and A. P. Litman

**LEGAL NOTICE**

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

JUNE 1970

OAK RIDGE NATIONAL LABORATORY  
Oak Ridge, Tennessee  
operated by  
UNION CARBIDE CORPORATION  
for the  
U.S. ATOMIC ENERGY COMMISSION

—

.

.

—

.

.

.

.

—

## CONTENTS

	<u>Page</u>
Abstract . . . . .	1
Introduction . . . . .	1
Experimental Methods and Materials . . . . .	3
Results . . . . .	7
Effect of Salt Composition and BF <sub>3</sub> Pressure (Series I) . . . . .	7
Weight Changes . . . . .	7
Salt Chemistry . . . . .	8
Specimen Chemistry . . . . .	10
Metallography . . . . .	11
Effect of Temperature (Series II) . . . . .	13
Interpretation of Corrosion Rates . . . . .	14
Conclusions . . . . .	16
Acknowledgment . . . . .	17



.

.

.

.

.

.



COMPATIBILITY WITH FUSED SODIUM FLUOROBORATES AND  
BF<sub>3</sub> GAS OF HASTELLOY N ALLOYS

J. W. Koger and A. P. Litman<sup>1</sup>

ABSTRACT

Corrosion by NaBF<sub>4</sub>-NaF mixtures (4-8 mole % NaF) low in oxygen and water was studied with 6800-hr static tests at 605°C in standard Hastelloy N capsules with titanium-modified Hastelloy N specimens. Boron trifluoride gas was added to overpressures up to 400 psig. Specimens in the molten salts and at the interface showed both weight gains and losses. The gains decreased with increasing NaBF<sub>4</sub> content, and losses up to 0.03 mg/cm<sup>2</sup> (< 0.01 mil/year) were observed for specimens in 4 mole % NaF. Weight changes of specimens in vapor were very small and independent of overpressure. The main reaction was the oxidation of chromium in the alloy by iron fluoride in the salt to form Na<sub>3</sub>CrF<sub>6</sub> and deposit iron on both specimens and capsule. Metallographic examination showed only minor attack and no difference in the two Hastelloy N alloys.

The rate of chromium depletion at 605°C was consistent with the rate of solid-state diffusion of chromium to the alloy surface. Additional tests from 538 to 760°C showed Arrhenius behavior that confirmed this mechanism.

Fluoroborate salt mixtures were found compatible with Hastelloy N alloys under the conditions of these experiments, and comparison with other experiments showed that increases in water and oxygen content increased the chromium uptake and corrosion.

---

INTRODUCTION

The successful use of molten fluoride salts in a reactor system, as demonstrated by the Molten Salt Reactor Experiment (MSRE) at the Oak Ridge National Laboratory, has led to development studies for a Molten Salt Breeder Reactor (MSBR). One of the most promising features of molten salts has been the low corrosion rates experienced with materials of construction, principally nickel-base alloys.

---

<sup>1</sup>Now with AEC Division of Space Nuclear Systems, Washington, D.C.

Theory and experiment<sup>2</sup> have shown that the corrosion resistance of metals to molten fluoride salts varies directly with the "nobility" of the metal; that is, the resistance to attack varies inversely with the magnitude of the free energy of formation of the fluorides of metals in the container material. Therefore, the container alloy for the fluoride salt must have only a small percentage of constituents that are easily oxidized by the components of the salt. Considering these facts and utilizing information gained in corrosion testing of commercial alloys, ORNL developed<sup>3</sup> a high-strength nickel-base alloy, Hastelloy N, containing 17% Mo, 7% Cr, and 5% Fe, for use in the MSRE. These early experiments, as well as many recent corrosion tests<sup>4-6</sup> in LiF-BeF<sub>2</sub>-ThF<sub>4</sub>, LiF-BeF<sub>2</sub>-UF<sub>4</sub>, and LiF-BeF<sub>2</sub>-UF<sub>4</sub>-ThF<sub>4</sub>, have shown that Hastelloy N is very resistant to attack and corrosion rates are below 0.1 mil/year.

Recently the selection of a fluoride salt that can be used as a coolant to transfer heat from the fuel salt to a steam power conversion system has been seriously considered. Cost and melting point considerations favor the sodium fluoroborate mixture, NaBF<sub>4</sub>-8 mole % NaF. However, little information exists on corrosion by fluoroborates. Initial corrosion results were obtained from an impure fluoroborate salt (high in oxygen and water) in thermal convection loop tests,<sup>7</sup> but these results were not considered indicative of behavior with purer salt. Since that time, new methods of preparation have greatly increased the purity of available salt with respect to oxygen and water.

---

<sup>2</sup>J. H. DeVan and R. B. Evans III, Corrosion Behavior of Reactor Materials in Fluoride Salt Mixtures, ORNL-TM-328 (Sept. 19, 1962).

<sup>3</sup>W. D. Manly, J. H. Coobs, J. H. DeVan, D. A. Douglas, H. Inouye, P. Patriarca, T. K. Roche, and J. L. Scott, "Metallurgical Problems in Molten Fluoride Systems," Progr. Nucl. Energy Ser. IV 2, 164-179 (1960).

<sup>4</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Feb. 29, 1968, ORNL-4254, pp. 218-221.

<sup>5</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Aug. 31, 1968, ORNL-4344, pp. 257-264.

<sup>6</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Feb. 28, 1969, ORNL-4396, pp. 243-246.

<sup>7</sup>J. W. Koger and A. P. Litman, Compatibility of Hastelloy N and Croloy 9M with NaBF<sub>4</sub>-NaF-KBF<sub>4</sub> (90-4-6 mole %) Fluoroborate Salt, ORNL-TM-2490 (April 1969).

The overall objective of this study was to determine the corrosion characteristics of pure (low oxygen and water)  $\text{NaBF}_4$ - $\text{NaF}$  mixtures under isothermal conditions. Of particular concern was the temperature-dependent dissociation of the salt into liquid  $\text{NaF}$  and  $\text{BF}_3$  gas. Thus, we first determined the effects of varying the concentration of our salt mixture and the  $\text{BF}_3$  pressure over it in 6800-hr tests at  $605^\circ\text{C}$ . In a later series of experiments we determined the rate of chromium uptake by  $\text{NaBF}_4$ -8 mole %  $\text{NaF}$  between  $538$  and  $760^\circ\text{C}$  in 1200-hr tests.

#### EXPERIMENTAL METHOD AND MATERIALS

The capsule design used in studying the effect of salt composition and  $\text{BF}_3$  overpressure (Series I) is pictured in Fig. 1. Each capsule contained three specimens of titanium-modified Hastelloy N, one located in the vapor space, one in the salt, and one at the liquid-vapor interface. The capsule was constructed of commercial Hastelloy N and was 2 in. in diameter  $\times$  6 in. high. The titanium-modified alloy is considered because of its superior radiation-resistant properties.




Fig. 1. Hastelloy N Capsule Assembly for Studying Effects of Salt Composition and  $\text{BF}_3$  Overpressure.

The capsule used in studying the effect of temperature (Series II) was basically the same. However, the test specimens were commercial Hastelloy N in the form of 0.030-in.-thick strips to provide more surface area. Each capsule was 2 in. in diameter  $\times$  8.5 in. high and contained 16 specimens. The capsule is pictured in Fig. 2, and the test specimens are shown in Fig. 3. Table 1 lists the compositions of the alloys used for the capsules and specimens.






Fig. 2. Hastelloy N Capsule Assembly for Temperature Effect Study.



(a)



(b)

Fig. 3. Standard Hastelloy N Specimens Made to Provide Maximum Surface Area for Study of Temperature Effects. (a) End view. (b) Side view.



Table 1. Composition of Hastelloy N

Test Series	Component	Composition (wt %) <sup>a</sup>					
		Mo	Cr	Fe	Si	Mn	Ti
I	Capsules	15.8	7.4	2.4	0.2	0.3	0.02
	Specimens	12.0	7.3	< 0.1	< 0.01	0.14	0.5
II	Capsules and Specimens	17.0	7.2	4.3	0.45	0.5	0.02

<sup>a</sup>Balance nickel.

The salt for these tests was processed by the Fluoride Processing Group of the Reactor Chemistry Division. The very pure (> 99.9%) starting materials were evacuated to about 380 torr, heated to 150°C in a vessel lined with nickel, and then held for about 15 hr under these conditions. After the rise in vapor pressure was observed to be not excessive (indicating no volatile impurities), the salt was heated to 500°C while still under vacuum and agitated by bubbling helium through the capsule for a few hours. The salt was then transferred to the fill vessel and forced into the capsules with helium pressure. Salt chemistry is discussed under "Results" in this report.

All capsules were heated in vertical muffle furnaces (Fig. 4) and monitored with Chromel-P vs Alumel thermocouples, which had been spot welded to the capsule and covered with shim stock. In our first series of tests all capsules were operated at 605°C, close to the maximum temperature proposed for the coolant salt in the MSBR. Capsule 1 of this series contained a helium overpressure of 4 psig and no added BF<sub>3</sub>. Capsules 2, 3, and 4 contained BF<sub>3</sub> corresponding to overpressures of 50, 100, and 400 psig, respectively. Initially the added BF<sub>3</sub> dissolved in the molten salt or combined with the NaF, but after a few minutes the pressure in the capsule gradually increased. However, when the capsules had been pressurized to the operating pressures, no changes in BF<sub>3</sub> content were necessary during the test. The compositions of the salts calculated from amounts of BF<sub>3</sub> added are shown in Table 2.

Photo 76727




Fig. 4. Furnace Assembly.

Table 2. Effect of Salt Composition and  $\text{BF}_3$  Overpressure on Weight Changes of Hastelloy N

Capsule	$\text{BF}_3$ Overpressure (psig)	Salt Composition (mole %)		Weight Change ( $\text{mg}/\text{cm}^2$ )		
		$\text{NaBF}_4$	NaF	Vapor	Interface	Liquid
1	0	92	8	-0.03	+0.5	+1.3
2	50	94	6	-0.3	+0.4	+1.2
3	100	95	5	-0.4	+0.2	+0.06
4	400	96	4	0.0	-0.03	-0.03

After 6800 hr the salt in each capsule was removed and sampled. The capsules were opened and the specimens were removed, washed in warm distilled water, dried with ethyl alcohol, and weighed. The specimens and capsules were examined metallographically and by x-ray fluorescence and microprobe analysis. The salts were analyzed before and after the tests.

In our second series of experiments, the capsules were operated at  $427^\circ\text{C}$  ( $800^\circ\text{F}$ ),  $538^\circ\text{C}$  ( $1000^\circ\text{F}$ ),  $649^\circ\text{C}$  ( $1200^\circ\text{F}$ ), and  $760^\circ\text{C}$  ( $1400^\circ\text{F}$ ) with 5 psig He overpressure and calculated equilibrium  $\text{BF}_3$  pressures of 0.005, 0.07, 0.5, and 2.5 psia, respectively. After 1200 hr the salt in each capsule was removed and sampled for analysis. The salt had also been analyzed before test.

## RESULTS

### Effect of Salt Composition and $\text{BF}_3$ Pressure (Series I)

#### Weight Changes

The compositional changes in the salt effected by  $\text{BF}_3$  gas additions in our first series of tests caused a measurable difference in the weight changes of our test specimens. As shown in Table 2, the weight changes were relatively small, and some specimens showed weight gains instead of the expected losses. There was no correlation between the pressure of  $\text{BF}_3$  and the weight change of the specimens exposed to the vapor.

The specimens immersed in salt in capsules 1, 2, and 3 showed progressively decreasing weight gains. The salt specimen in capsule 4 showed a weight loss equivalent to a corrosion rate less than 0.01 mil/year. The same weight change pattern was observed for the specimens at the interface. Thus, the weight gain of specimens in the liquid and at the interface increased as the amount of  $\text{NaBF}_4$  in the salt decreased.

Figure 5 shows the specimens after test. Very little corrosion was noted at any position on the specimens or capsules.




Fig. 5. Titanium-Modified Hastelloy N Specimens After Exposure to  $\text{NaBF}_4$ -8 mole % NaF at  $605^\circ\text{C}$  for 6800 hr. Numbers identify capsules.

### Salt Chemistry

Chemical analyses of the salt before and after test for each capsule are given in Table 3. The most significant changes are an increase in chromium concentration and a decrease in iron concentration. No titanium concentrations are included in Table 3 because, as expected,

Table 3. Salt Analyses Before and After Test (Series I)


Element	Concentration				
	As Received	Capsule 1	Capsule 2	Capsule 3	Capsule 4
	<u>Weight Percent</u>				
Na	21.9	21.4	21.0	21.8	21.0
B	9.57	9.54	9.48	9.48	9.49
F	68.2	69.2	68.5	68.7	68.8
	<u>Parts Per Million</u>				
Cr	19	75	75	73	72
Ni	28	< 10	< 10	< 10	< 10
Fe	223	24	28	29	22
Mo	< 10	< 5	< 5	< 5	< 5
O	459	194	576	372	1420 <sup>a</sup>
H <sub>2</sub> O	400	400	460	350	460

<sup>a</sup>Questionable result.

no change was noted; only the test specimens contained titanium, and they constituted only a small part of the total system. The only change in the water and oxygen concentrations occurred in capsule 4. The high oxygen concentration reported for this capsule would normally have produced highly oxidizing conditions<sup>8</sup> and high corrosion rates. The reported value is believed to be in error because close examination of the system disclosed no leaks or signs of oxidation. Apparently some BF<sub>3</sub> escaped from the capsules after cooling and during opening, since the concentrations of sodium, boron, and fluorine in the salt were about the same in the final analysis of each capsule.

The increase in chromium and the decrease in iron in the salt suggest a reaction of the type

<sup>8</sup>H. E. McCoy, J. R. Weir, Jr., R. L. Beatty, W. H. Cook, C. R. Kennedy, A. P. Litman, R. E. Gehlbach, C. E. Sessions, and J. W. Koger, Materials for Molten-Salt Reactors, ORNL-TM-2511 (May 1969).



where (s) indicates solid solution in Hastelloy N and (d) indicates dissolved in salt. Any water or oxygen-type impurity in the salt would also have caused some oxidation of the container materials, but these impurities appear to have been negligible in this series of tests. Because the salt in these experiments contained NaF, the chromium fluoride in the corrosion product was found as  $\text{Na}_3\text{CrF}_6$ . This material has also been identified in other corrosion experiments<sup>9</sup> and its crystal structure has been determined by x-ray diffraction analysis.<sup>10</sup> Also, the iron fluoride in these experiments may have existed as  $\text{Na}_3\text{FeF}_6$ , but this compound was not identified.

### Specimen Chemistry

The proposed corrosion reaction was verified further by x-ray fluorescence analysis of the specimens. Table 4 gives the composition of the near-surface region of a specimen from capsule 4. The composition was determined by comparing x-ray intensities with those of a specimen not exposed to salt or vapor. For any given region in the capsule, the qualitative results from all the specimens were quite similar. These results show a depletion of chromium and enrichment of iron in the near-surface region. All specimens also showed a loss of titanium. Microprobe analysis showed essentially the same surface changes. A chromium gradient was seen but was so small that we could not distinguish between edge effects and an actual gradient.

According to Cantor,<sup>11</sup>  $\text{NaBF}_4$ -8 mole % NaF may also oxidize chromium by the reactions

---



<sup>9</sup>J. W. Koger and A. P. Litman, Compatibility of Hastelloy N and Croloy 9M with  $\text{NaBF}_4$ -NaF- $\text{KBF}_4$  (90-4-6 mole %) Fluoroborate Salt, ORNL-TM-2490 (April 1969).

<sup>10</sup>G. Brunton, "The Crystal Structure of  $\text{Na}_3\text{CrF}_6$ ," Mater. Res. Bull. 4, 621-626 (1969).

<sup>11</sup>S. Cantor, MSR Program Semiann. Progr. Rept. Aug. 31, 1968, ORNL-4344, p. 160.

Table 4. Composition of Near-Surface Regions of Test Specimens as Determined by X-Ray Fluorescent Analysis

Exposure Conditions	Concentration (wt %)				
	Mo	Ni	Fe	Cr	Ti
Unexposed	12.0	79.9	0.1	7.5	0.5
Vapor	12.3	79.2	0.13	7.1	0.19
Interface	13.7	69.6	13.4	3.0	0.2
Liquid	18.0	22.7	56.4	2.7	0.16



However, no borides were identified either on our specimens or in the salt, and the experimental evidence that iron replaced the chromium indicates that reaction (1) rather than (2) was the predominant mode of chromium oxidation. If essentially no iron fluoride compound were present in the melt, reaction (2) could well control the corrosion process.

### Metallography

Figure 6 shows the microstructure of the specimen from the vapor region of capsule 1. There was some indication of a very thin, discontinuous deposit at the surface in the as-polished condition. After etching, this deposit was no longer visible. Figure 7 shows the specimen that was exposed to salt in capsule 1. A deposit is visible on the as-polished specimen. Etching again removed the deposit but in this case produced considerable attack at the exposed surface. Metallographic observation of the capsule wall showed similar behavior. This deposit is apparently iron rich, and the area revealed by the etchant is chromium-depleted Hastelloy N. Thus, no difference in the behavior of titanium-modified and standard Hastelloy N was noted in this test. The interface between the salt and gas could be seen on the capsule, but no attack was noted there.




Fig. 6. Titanium-Modified Hastelloy N from Capsule 1 Exposed to  $\text{BF}_3$  Vapor for 6800 hr at  $605^\circ\text{C}$ . Weight change,  $+0.03 \text{ mg/cm}^2$ . 500 $\times$ . (a) As polished. (b) Etched with glyceria regia.




Fig. 7. Titanium-Modified Hastelloy N from Capsule 1 Exposed to  $\text{NaBF}_4$ -8 mole %  $\text{NaF}$  for 6800 hr at  $605^\circ\text{C}$ . Weight change,  $+1.3 \text{ mg/cm}^2$ . 500 $\times$ . (a) As polished. (b) Etched with glyceria regia.



Effect of Temperature (Series II)

Our second series of tests was designed to determine the effects of temperature on chromium mass transfer from the Hastelloy N to the salt. The salt was analyzed before and after test to determine impurity pickup. The  $\text{NaBF}_4$ -8 mole % NaF contained approximately 400 ppm each of oxygen and water before and after test. The chromium concentration in the salt increased while the iron decreased, as seen in Table 5. No changes in the concentration of nickel and molybdenum were noted. Again, the results suggest chromium oxidation by reduction of an iron fluoride compound. Metallography of Hastelloy N from this test showed, after etching, no attack of the specimen (Fig. 8).

Table 5. Analysis of Salt for Impurities Before and After Test (Series II)

Impurity	Average Concentration <sup>a</sup> (ppm)				
	As Received	Capsule 1	Capsule 2	Capsule 3	Capsule 4
Cr	15	45	87	225	575
Fe	200	190	180	150	40
O	460	430	450	412	550
H <sub>2</sub> O	320	400	530	480	490

<sup>a</sup>Nickel and molybdenum were not detected (< 10 ppm) in any samples.



Fig. 8. Hastelloy N Exposed to  $\text{NaBF}_4$ -8 mole % NaF for 1200 hr at 760°C. Etched with glyceria regia, 500x.

## INTERPRETATION OF CORROSION RATES

If the chromium surface concentration remains constant (only true if the salt contains an excess of iron) at any given point in the capsule, the amount of chromium leaving a capsule in Series I is given by the equation<sup>1,2</sup>

$$\Delta W = 2\rho(C_0 - C_s) \sqrt{Dt/\pi} , \quad (4)$$

where

$\Delta W$  = integral flux of Cr leaving metal, g/cm<sup>2</sup>

$\rho$  = density of metal, g/cm<sup>3</sup>

$C_0$  = initial weight fraction of Cr

$C_s$  = surface weight fraction of Cr

$D$  = diffusion coefficient of Cr in alloy, cm<sup>2</sup>/sec

$t$  = exposure time, sec.

Using the following information

Salt in capsule = 282 g

Cr increase in salt = 55 ppm (by weight)

Capsule surface area = 142 cm<sup>2</sup>

to obtain  $\Delta W$  and then using

$C_0 = 7.5\%$

$C_s = 0$  (consistent with excess of Fe)

$\rho = 8.8$  g/cm<sup>3</sup>

$t = 6800$  hr,

we obtain

$D_{\text{calcd}} = 3.3 \times 10^{-15}$  cm<sup>2</sup>/sec at 605°C.

This compares favorably with  $3 \times 10^{-15}$  cm<sup>2</sup>/sec at 605°C extrapolated from the range 700 to 850°C from data<sup>1,3</sup> of DeVan and Evans for chromium

<sup>1,2</sup>L. S. Darken and R. W. Gurry, Physical Chemistry of Metals, McGraw-Hill, New York, 1953.

<sup>1,3</sup>W. R. Grimes, G. M. Watson, J. H. DeVan, and R. B. Evans, "Radio-Tracer Techniques in the Study of Corrosion by Molten Fluorides," pp. 559-574 in Conference on the Use of Radioisotopes in the Physical Sciences and Industry, September 6-17, 1960, Proceedings, Vol. III, International Atomic Energy Agency, Vienna, 1962.

diffusion in Hastelloy N. From this comparison, we conclude that the controlling rate mechanism in this experiment was the solid-state diffusion of chromium in the alloy and that the oxidation potential of the salt was established by the presence of iron fluoride.

Figure 9 shows the variation of chromium content with test temperature for the experiments of Series II. Included for comparison are chromium concentrations measured in loop tests after 1200 hr at various H<sub>2</sub>O impurity levels.<sup>14-17</sup> An Arrhenius-type relationship appears to

<sup>14</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Feb. 29, 1968, ORNL-4254, pp. 218-221.

<sup>15</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Aug. 31, 1968, ORNL-4344, pp. 257-264.

<sup>16</sup>J. W. Koger and A. P. Litman, MSR Program Semiann. Progr. Rept. Feb. 28, 1969, ORNL-4396, pp. 243-246.

<sup>17</sup>J. W. Koger and A. P. Litman, Compatibility of Hastelloy N and Croloy 9M with NaBF<sub>4</sub>-NaF-KBF<sub>4</sub> (90-4-6 mole %) Fluoroborate Salt, ORNL-TM-2490 (April 1969).




Fig. 9. Temperature Dependence of Chromium Concentration in Sodium Fluoroborate Salt.

hold between 538 and 760°C. This would be expected if the rate of chromium buildup in the salt were controlled by solid-state diffusion of chromium to the capsule wall. Using diffusion data for chromium in Hastelloy N obtained by DeVan and Evans<sup>13</sup> and assuming the chromium surface concentration to have been reduced to zero by the salt, we predict a chromium buildup shown by the dashed line in Fig. 9. The agreement between the slopes (activation energy) of the predicted and experimental curves, although not exact, gives credence to the assumption that chromium mass transfer to the salt is limited by solid-state diffusion of chromium to the Hastelloy N surface.

#### CONCLUSIONS

1. Titanium-modified Hastelloy N specimens were exposed for 6800 hr to isothermal  $\text{NaBF}_4$ -NaF salt mixtures containing only a few hundred parts per million oxygen and water and varying in composition from 4 to 8 mole % NaF. Specimens in the vapor region lost weight in all but the 96 mole %  $\text{NaBF}_4$  mixture. Specimens fully immersed in the salt gained weight in all but the 96 mole %  $\text{NaBF}_4$  mixture. The weight gains decreased as the  $\text{NaBF}_4$  content of the salt increased.
2. No differences in the corrosion of specimens in the vapor region were noted as a function of  $\text{BF}_3$  overpressure to 400 psig.
3. In the main corrosion reaction, chromium from the alloy was oxidized by iron fluoride impurities initially in the salt. The iron that was reduced deposited on the specimens and capsule.
4. Metallographic observation of both standard Hastelloy N capsules and titanium-modified Hastelloy N specimens showed very little attack, although a thin discontinuous deposit rich in iron was observed at the surface of specimens exposed to vapor.
5. A diffusion coefficient for chromium in Hastelloy N calculated from the rate of chromium removal from standard Hastelloy N by  $\text{NaBF}_4$ -8 mole % NaF held between 538 and 760°C agreed well with an extrapolation of published results. Thus, solid-state diffusion of chromium appeared to be the rate-controlling mechanism for corrosion in these tests.

6. Under the condition of these experiments, the fluoroborate salt mixtures were compatible with the Hastelloy N alloys. By virtue of other experiments we conclude that increases in water as impurity increase the chromium uptake and the corrosion.

#### ACKNOWLEDGMENT

We wish to acknowledge E. J. Lawrence for his expert supervision of the fabrication, operation, and disassembly of the test capsules and F. D. Harvey for his handling of the test specimens. We are also indebted to H. E. McCoy, Jr., J. H. DeVan, and C. E. Sessions for constructive review of the manuscript.

Special thanks are extended to H. R. Gaddis and Helen Mateer of the General Metallography Group, Harris Dunn and others in the Analytical Chemistry Division, Graphic Arts, and the Metals and Ceramics Division Reports Office for invaluable assistance.



## INTERNAL DISTRIBUTION

- |       |   |        |                   |
|-------|---|--------|-------------------|
| 1-3.  | Central Research Library                                    | 47.    | W. O. Harms       |
| 4-5.  | ORNL - Y-12 Technical Library<br>Document Reference Section | 48.    | P. N. Haubenreich |
| 6-15. | Laboratory Records Department                               | 49.    | R. E. Helms       |
| 16.   | Laboratory Records, ORNL RC                                 | 50-52. | M. R. Hill        |
| 17.   | ORNL Patent Office  | 53.    | W. R. Huntley     |
| 18.   | MSRP Director's Office (Y-12)                               | 54.    | H. Inouye         |
| 19.   | G. M. Adamson, Jr.  | 55.    | P. R. Kasten      |
| 20.   | J. L. Anderson  | 56-65. | J. W. Koger       |
| 21.   | R. F. Apple   | 66.    | E. J. Lawrence    |
| 22.   | C. F. Baes  | 67.    | R. B. Lindauer    |
| 23.   | S. E. Beall   | 68.    | M. I. Lundin      |
| 24.   | E. S. Bettis  | 69.    | R. E. MacPherson  |
| 25.   | F. F. Blankenship   | 70.    | W. R. Martin      |
| 26.   | E. G. Bohlmann  | 71.    | H. E. McCoy, Jr.  |
| 27.   | R. B. Briggs  | 72.    | C. J. McHargue    |
| 28.   | S. Cantor   | 73.    | A. S. Meyer       |
| 29.   | O. B. Cavin   | 74.    | D. M. Moulton     |
| 30.   | Nancy C. Cole   | 75.    | P. Patriarca      |
| 31.   | W. H. Cook  | 76.    | A. M. Perry       |
| 32.   | J. L. Crowley   | 77.    | H. C. Savage      |
| 33.   | F. L. Culler  | 78.    | Dunlap Scott      |
| 34.   | J. H. DeVan   | 79.    | J. L. Scott       |
| 35.   | J. R. DiStefano   | 80.    | C. E. Sessions    |
| 36.   | S. J. Ditto   | 81.    | J. H. Shaffer     |
| 37.   | W. P. Eatherly  | 82.    | G. M. Slaughter   |
| 38.   | J. I. Federer   | 83.    | A. N. Smith       |
| 39.   | D. E. Ferguson  | 84.    | D. A. Sundberg    |
| 40.   | L. M. Ferris  | 85.    | J. R. Tallackson  |
| 41.   | J. H. Frye, Jr.   | 86.    | R. E. Thoma       |
| 42.   | R. E. Gehlbach  | 87.    | D. B. Trauger     |
| 43.   | L. O. Gilpatrick  | 88.    | G. M. Watson      |
| 44.   | W. R. Grimes  | 89.    | J. R. Weir, Jr.   |
| 45.   | A. G. Grindell  | 90.    | J. C. White       |
| 46.   | F. D. Harvey  | 91.    | Gale Young        |
|       |   | 92.    | E. L. Youngblood  |

## EXTERNAL DISTRIBUTION

- 93-94. D. F. Cope, RDT, SSR, AEC, Oak Ridge National Laboratory
95. A. R. DeGrazia, Division of Reactor Development and Technology, AEC, Washington
96. David Elias, Division of Reactor Development and Technology, AEC, Washington
97. J. E. Fox, Division of Reactor Development and Technology, AEC, Washington

98. Norton Haberman, Division of Reactor Development and Technology, AEC, Washington
99. Kermit Laughon, RDT, OSR, AEC, Oak Ridge Operations
- 100-109. A. P. Litman, Division of Space Nuclear Systems, AEC, Washington
- 110-111. T. W. McIntosh, Division of Reactor Development and Technology, AEC, Washington
112. D. R. Riley, Division of Reactor Development and Technology, AEC, Washington
113. M. Shaw, Division of Reactor Development and Technology, AEC, Washington
114. J. M. Simmons, Division of Reactor Development and Technology, AEC, Washington
115. Laboratory and University Division, AEC, Oak Ridge Operations
- 116-130. Division of Technical Information Extension